

FIBRANgyps JF Hydro

Joint filler

Datasheet



Description

FIBRANgyps JF Hydro is a jointing compound consisting of a mixture of selected gypsum, aggregates and chemical additives that give the mixture a plastic appearance. In powder form, with high moisture resistance and low water absorption, ideal for the grouting of water-repellent slabs. Suitable as a first and second coat and joint shaving. CE marked according to EN 13963:2014, 3B standard type.

Packaging: 10 kg bags.

Applications

Especially suitable for grouting the joints and screw heads of slabs with reduced water absorption such as FIBRANgyps H and FIBRAN SUPER, as well as for the repair of damaged small plaster or damaged gypsum plasterboard, in the installation of corner protectors and the finishing of internal corners with microperforated interior corners with micro-perforated tape. Thanks to its excellent adhesion to the substrate it can also be used on glass fibre-coated boards such as FIBRAN NEXT in damp indoor areas and in outdoor areas not exposed directly exposed to the weather (e.g. pilotis floors).

Features	U.M.	Value	Standard
Reaction to fire	Class	A1	EN 13501-1
Working time	min	60/70*	EN 13963
Setting time	min	80/90*	EN 13963
Water/gypsum ratio	-	100/165	-
Coverage	Kg/m ²	0,39	-
Preparation	-	Suitable for mixing by hand or mechanical whisk	-

*indicative times, varying according to weather conditions

Storage

Store in a cool, dry and not ventilated. Keep packaging intact. Use within 9 months after date of production.

Warning

The product must be used at temperatures between 5 and 35°C. At lower temperatures the drying becomes too slow, and the product can be damaged by frost. At higher temperatures, drying too quickly can cause micro-cracking. Avoid strong temperature fluctuations during the setting phase. After application, rooms must be ventilated to allow proper drying.

FIBRAN S.p.A. reserves the right to modify or change the technical data given without prior notice. It is the customer's responsibility to check that the technical information is suitable for the specific intended use. For further technical information please consult www.fibran.it or the Technical Department by writing to tech@fibran.it.